

LOBADUR® ProColor

Solvent based, odorless coloring for the professional staining of parquet and hardwood floors.

Article No.:	11012
Gloss Level:	n/a
Package Size:	0,75 Liter
Giscode:	G1
Solids:	9 ± 4% depending on tint ,37 ± 3% on white and papyrus
Viscosity DIN 4:	Not defined

Range of Use: For the professional coloring – staining of parquet and hardwood floors for recoating with waterborne systems.
Preferably stain wood types with large pores (e.g. oak, ash).
On wood with small pores sanding marks will be easily visible.
The color tints are mostly based on the natural color of tropical wood. We recommend to lay the color samples on the original wood and compare after finishing. Colors in stock are: Bilinga, Jatoba, Kambala, Mahogani, Papyrus, Smoked Oak, Black, Sucupira, White, Wengé and Transparent.
The colors are inter- mixable. Other colors or special colors are available on request.

Information on Use:

- Stir material well
- Trowel fill with a stainless trowel, alternatively apply as thin as possible with an oil brush
- Use a single disc grinder and the beige abrasive pad thoroughly until an even surface develops
- Alternatively use a fuss free cotton cloth to roughen and buff the area
- Work in sections
- Before using LOBADUR® ProColor white on oak please check with our factory

Setup Recommendations: Wood and Parquet Floors:

1. Sand surface thoroughly, clean dust and apply LOBADUR® ProColor in sections, check the LOBA Information sheet “It all depends on the final cut”
2. Use the LOBATOOL normal pad (beige) until an even surface develops. Alternatively wipe off excess evenly using a cloth
3. Drying
4. Apply LOBADUR® waterbased finish in three coats using a roller
5. Intermediate sanding and roll final coat

Covering Tool:	LOBATOOL Oil Brush	LOBATOOL stainless trowel Fuzz free cotton cloth
Covering Quantity:	Oil brush ca. 40 – 50 ml/m ² (4 – 5 ml/square foot) White and papyrus ca.50ml/m ² (5 ml/square foot)	Trowel: 25 - 30 ml/m ² (2 – 3 ml/square foot) Cotton cloth 30 – 40 ml/m ² (3 – 4 ml/square foot) White and papyrus ca. 50 ml/m ² (5 ml/square foot)

Drying Time: Earliest recoating after 12 hours

Intermediate Sanding: Do not intermediate sand LOBADUR® ProColor .

Suitable Finishes for Recoating:	With reduced side bonding LOBADUR WS Global	Up to heavy wear: LOBADUR WS EasyFinish	Up to extremely heavy wear: LOBADUR WS 2K Supra LOBADUR WS 2K Duo
---	---	---	--

Thinner: The material is ready-to-use and cannot be diluted!

Storage and Transportation: Store in a cool and dry place; not sensitive to frost; storable for 18 months; non hazardous material according to ADR, white and papyrus N – dangerous to the environment
Weiß und Papyrus N – Umweltgefährlich

The general informaton on the use of strongly solvent based LOBADUR® products must be noticed.