

Technical Information



LOBADUR® WS Argo

Additive to prolong the drying time of LOBADUR® Wasserlacken .

Article No.: 11015
Gloss Level: n/a
Package Size: 250ml

- Range of Use:** LOBADUR® WS Argo prolongs the drying of waterborne finishes and therefore reduces the risk of lump development and improves the flow of the product. The viscosity of the finishes remains to a great extent. Suitable for the use in unfavourable climatic conditions, like high temperatures and/or low air humidity.
- Information on Use:** LOBADUR® WS Argo can be added to LOBADUR® waterbased finish up to a maximum of 5%. Mix, at the most, one package of LOBADUR® WS Argo with 5l (5kg) of finish.
- Application:** Add LOBADUR® WS Argo only right before the application by shaking or stirring thoroughly. When using 2-component-systems (LOBADUR® WS 2K Duo, LOBADUR® WS 2K Supra, LOBADUR® WS 2K Ultra) add LOBADUR WS Argo only AFTER adding hardener to the mass!
- Finishes mixed with LOBADUR® WS Argo must be used within 24 hours, 2-component-systems within 2 hours. A longer storage time can not be guaranteed.
- Drying Time:** The drying time of the mixed finishes will increase. A recoating will be possible after 6 to 8 hours. Can be carefully walked on after 6 – 8 hours, light wear after 24 hours, reaches final hardness after ca. 8 days.
- Storage and Transportation:** Not sensitive to frost, no limited storage time, not a hazardous material according to ADR.

The Technical Information of the stated finishes and the general information on the use of strongly solvent based LOBADUR® products must be noticed.

LOBA GmbH & Co. KG
Tel: +49 (0) 7156 357 169
Fax: + 49 (0) 7156 357 211
Mail: service@loba.de

revised: 27.08.2008 DK